

Guiding formulations for general industrial coatings (Solvent-based)

Internal reference: Formulations 2	Kronos 2310	Color Black FW 200	Special Black 100	Bayferrox Yellow 3920	Hostaperm Yellow H6G	Novoperm Orange HL70	Bayferrox Red 130M	Novoperm Red F3RK 70	Hostaperm Rosa E	Heliogen Blue L7072D
Aldehyde resin* (60% in Solvesso 100)	17.0	33.9	31.5	20.6	25.4	24.5	18.0	24.5	28.5	24.5
DELTA-DC® 3046 (40% active)	3.4	11.8	12.9	4.2	15.4	16.6	4.8	10.2	8.9	12.4
DELTA-S® 5745 (Synergist additive)	--	0.5	0.5	--	--	--	--	--	--	0.5
Bentone 27	1.0	--	--	1.0	--	--	1.0	--	--	--
Methoxypropylacetete (MPA)	4.8	19.9	13.1	9.6	14.1	12.7	4.6	13.4	20.3	20.3
Solvesso 100	4.8	19.9	13.0	9.6	14.1	12.7	4.6	13.4	20.3	20.3
Pigment	69.0	14.0	29.0	55.0	31.0	33.5	67.0	38.5	22.0	22.0
Total weight	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Pigment color index	PW 6	PBk 7	PBk 6	PY 42	PY 175	PO 36	PR 101	PR 170	PR 122	PB 15:2

* e.g Laropal A81 (BASF)