

## Technical Data Sheet

Last revised: 01-2019

---

### MORDRY® 320

**MORDRY® 320** is a stabilizer ready-to-use cobalt/zirconium/calcium drier.

---

#### **Specifications:**

Composition	: Mixture of metal carboxylates in mineral spirit
Cobalt metal content	: 1.0%
Specific gravity @ 20°C	: 0.85 – 1.00 g/cm <sup>3</sup>
Color (visual)	: Blue-Violet

Methods of analysis can be received upon request

---

#### **Applications and usage:**

**MORDRY® 320** is a stabilized, ready-to-use blend of cobalt, zirconium and calcium suitable for use in a wide range of decorative paint systems. **MORDRY® 320** is a single addition pre-blend drier system dissolved in mineral spirit. The pre-stabilized mixed drier can eliminate problems associated with coatings such as gelling or instability resulting in degradation of drying performance. **MORDRY® 320** offers also a cost benefit in addition to its ease of use and reduction of stock levels.

The normal use level range for **MORDRY® 320** is between **2.0%** and **8.0%** calculated on resin solids.

This dose can be considered as a guideline. The optimum combination and concentrations will depend on the total formulation characteristics.

---

#### **Safety and Handling:**

**MORDRY® 320** should be handled in accordance with good industrial practice. Detailed information can be found in the Safety Data Sheet.

---

#### **Storage:**

**MORDRY® 320** should be stored at temperatures between 5 °C and 32 °C. Although **MORDRY® 320** will not freeze under ordinary conditions, best results can be insured if it is kept between the recommended temperatures prior to use. When kept in an original unopened container, it will keep up to 2 years from the date of manufacture. The production date is indicated on the container.

---

#### **Packaging:**

50 kg and 195 kg non-returnable metallic containers.

---